

気 温 表 (宮崎地方気象台、高鍋測候所)

「日平均気温・打設後28日後の平均気温」

(2014年～2023年)

月 日	1月		2月		3月		4月		5月		6月		7月		8月		9月		10月		11月		12月	
	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後
1	5.7	7.4	8.4	8.5	11.6	12.0	14.9	15.9	18.0	19.4	20.9	22.3	24.5	26.0	27.5	27.2	25.8	24.5	22.8	19.9	16.2	14.7	11.1	9.1
2	6.6	7.5	8.0	8.6	10.5	12.1	14.6	16.0	17.7	19.5	21.1	22.4	24.4	26.1	27.4	27.2	25.5	24.4	22.5	19.7	16.3	14.6	9.7	9.0
3	7.4	7.6	8.0	8.8	8.8	12.2	15.0	16.1	17.4	19.7	20.8	22.6	24.4	26.2	27.2	27.1	25.7	24.3	22.7	19.5	15.7	14.5	10.5	8.9
4	8.0	7.6	7.9	8.8	11.4	12.4	15.6	16.3	18.3	19.8	21.0	22.7	25.2	26.4	27.4	27.1	25.7	24.2	23.0	19.3	15.2	14.3	10.9	8.8
5	8.0	7.6	7.1	8.9	12.3	12.6	15.7	16.3	18.9	19.9	20.5	22.8	25.3	26.4	27.6	27.0	25.6	24.1	22.9	19.0	15.1	14.1	9.8	8.6
6	8.0	7.6	6.5	9.0	10.7	12.7	15.3	16.4	18.5	20.0	20.7	23.0	25.2	26.5	27.3	27.0	26.0	24.0	21.6	18.8	16.5	13.9	9.3	8.5
7	8.0	7.6	7.3	9.2	10.4	12.8	15.0	16.5	18.7	20.1	21.8	23.1	25.5	26.6	27.7	26.9	26.0	23.9	21.0	18.6	17.0	13.7	9.9	8.5
8	8.6	7.6	7.7	9.4	11.0	13.0	14.6	16.6	18.4	20.1	22.1	23.3	25.8	26.6	27.8	26.8	25.3	23.8	21.3	18.4	17.2	13.5	9.0	8.4
9	7.1	7.5	6.7	9.5	10.7	13.2	14.6	16.8	18.1	20.2	22.4	23.4	25.9	26.7	27.5	26.8	24.7	23.7	21.2	18.2	16.4	13.2	9.4	8.3
10	6.5	7.5	7.5	9.6	10.7	13.3	15.1	16.9	18.6	20.3	22.1	23.5	26.0	26.8	27.8	26.7	25.0	23.5	21.7	18.0	15.0	13.0	11.1	8.3
11	6.8	7.5	7.2	9.7	10.6	13.5	15.7	17.0	19.2	20.4	21.9	23.6	26.8	26.8	27.1	26.6	25.2	23.4	21.1	17.8	14.9	12.8	12.1	8.2
12	6.6	7.6	8.9	9.8	11.6	13.6	16.1	17.1	19.0	20.5	22.7	23.8	26.5	26.9	27.4	26.6	25.0	23.3	20.7	17.7	14.5	12.6	10.9	8.1
13	6.9	7.6	9.9	9.9	12.2	13.7	15.5	17.2	19.7	20.6	22.0	23.9	26.0	26.9	27.7	26.5	24.4	23.2	20.2	17.5	15.0	12.4	9.3	7.9
14	7.3	7.6	9.5	10.0	11.2	13.8	16.0	17.3	19.5	20.7	22.1	24.0	26.5	27.0	27.5	26.4	24.4	23.0	19.4	17.3	14.8	12.3	9.4	7.8
15	8.2	7.6	8.7	10.1	11.3	14.0	16.2	17.5	19.8	20.8	22.4	24.2	25.6	27.0	27.4	26.3	24.6	22.9	19.1	17.2	14.0	12.2	9.1	7.7
16	8.4	7.6	8.5	10.2	12.4	14.2	16.1	17.6	20.4	20.9	22.1	24.3	25.7	27.0	27.3	26.2	24.6	22.7	19.6	17.0	13.6	12.0	9.2	7.6
17	8.0	7.7	8.2	10.3	13.1	14.3	16.2	17.7	20.6	21.0	21.7	24.5	25.8	27.1	27.0	26.1	25.3	22.6	18.9	16.8	14.3	11.9	6.9	7.6
18	7.1	7.7	7.6	10.4	14.4	14.4	16.4	17.8	20.1	21.0	22.0	24.6	25.9	27.2	26.2	26.0	25.3	22.3	18.9	16.7	14.9	11.7	5.8	7.6
19	7.0	7.8	8.8	10.6	14.7	14.4	16.5	18.0	20.2	21.1	22.6	24.8	26.5	27.2	26.6	26.0	23.5	22.1	18.8	16.5	14.2	11.5	7.4	7.7
20	7.2	7.8	9.7	10.8	13.2	14.5	16.8	18.1	20.2	21.2	22.8	24.9	26.4	27.3	26.9	25.9	23.0	21.9	18.2	16.3	13.5	11.2	8.5	7.7
21	6.6	7.9	8.6	11.0	13.7	14.6	17.3	18.2	19.4	21.2	23.0	25.0	26.6	27.3	27.5	25.8	22.9	21.8	18.2	16.2	13.7	11.0	9.1	7.7
22	8.1	7.9	10.0	11.1	12.2	14.7	16.5	18.3	19.3	21.3	23.1	25.1	26.5	27.3	27.6	25.7	23.9	21.7	18.8	16.1	15.2	10.7	8.9	7.6
23	8.9	7.9	10.0	11.3	11.9	14.8	15.8	18.5	20.2	21.4	23.2	25.2	26.7	27.3	27.3	25.6	23.6	21.5	18.4	15.9	14.4	10.5	8.4	7.5
24	6.9	8.0	8.4	11.4	11.6	15.0	16.6	18.6	20.1	21.5	24.0	25.4	26.7	27.3	27.1	25.4	23.0	21.3	17.3	15.8	13.0	10.3	9.0	7.5
25	6.3	8.0	9.2	11.5	12.1	15.2	17.2	18.7	21.2	21.6	23.6	25.5	27.1	27.3	27.2	25.3	23.3	21.1	16.8	15.6	13.0	10.1	8.7	7.4
26	7.8	8.1	9.9	11.6	13.4	15.4	17.5	18.8	20.6	21.7	24.2	25.6	27.0	27.3	26.8	25.2	23.4	21.0	17.6	15.6	13.3	10.0	7.5	7.4
27	7.8	8.2	10.2	11.6	14.1	15.5	16.9	18.9	21.0	21.8	23.9	25.6	27.2	27.3	26.3	25.1	23.3	20.7	18.4	15.5	13.2	9.8	7.8	7.4
28	8.2	8.2	10.8	11.8	13.8	15.6	17.0	19.0	20.9	21.9	24.4	25.8	27.5	27.3	26.4	24.9	23.2	20.5	17.5	15.3	12.7	9.7	7.2	7.4
29	8.0	8.3	10.8	11.9	13.9	15.7	17.4	19.2	21.4	22.0	24.8	25.9	27.3	27.3	26.1	24.8	22.9	20.3	16.9	15.1	12.5	9.5	7.9	7.4
30	8.5	8.4			15.2	15.8	17.6	19.3	21.5	22.1	24.6	25.9	27.3	27.3	26.1	24.7	23.2	20.1	16.2	15.0	12.4	9.3	7.6	7.4
31	7.3	8.4			14.7	15.9			21.0	22.2			27.3	27.3	26.1	24.6			16.2	14.9			7.2	7.4

構造体強度補正值28Sの標準値 (セメントの種類: 普通ポルトランドセメント)		暑中コンクリート(修正標準配合)適用期間	
温度補正值	打込みから28日までの期間の予想平均気温 θ の範囲(°C)	コンクリートの打込み期間	日平均気温が25°Cを超える期間
3.0 N/mm ²	$8 \leq \theta$	1月24日～12月12日	7月4日～9月18日
6.0 N/mm ²	$0 \leq \theta < 8$	12月13日～1月23日	強度補正值: 6.0 N/mm ² (7月上旬～9月中旬)