

気 温 表 （宮崎地方気象台 高鍋観測所）

作成日:2025年 2月

過去10年間の高鍋地区日平均気温・コンクリート打設翌日から28日間の平均気温

測定期間:2015年 ～ 2024年

月 日	1月		2月		3月		4月		5月		6月		7月		8月		9月		10月		11月		12月	
	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後
1	5.3	7.4	8.1	8.8	11.4	11.9	15.1	16.1	18.0	19.4	20.8	22.4	24.9	26.2	27.5	27.3	25.9	24.7	23.0	20.0	16.3	14.8	10.6	9.1
2	6.6	7.5	7.5	8.9	9.8	12.0	14.7	16.2	17.6	19.5	21.0	22.5	25.1	26.3	27.5	27.3	25.6	24.6	22.4	19.8	16.6	14.7	10.2	9.0
3	7.5	7.6	7.3	9.0	8.5	12.2	15.2	16.3	17.3	19.6	20.9	22.6	24.9	26.4	27.4	27.2	25.7	24.6	22.5	19.6	16.1	14.5	10.9	8.9
4	7.4	7.5	7.9	9.1	11.4	12.4	16.1	16.4	18.4	19.8	20.9	22.8	25.6	26.5	27.6	27.2	25.6	24.5	22.9	19.4	15.8	14.3	11.0	8.8
5	7.8	7.6	7.8	9.1	12.5	12.6	15.9	16.5	19.2	19.8	20.3	22.9	25.8	26.5	27.7	27.1	25.6	24.4	22.9	19.1	15.3	14.1	10.1	8.6
6	8.4	7.6	6.9	9.2	11.2	12.6	15.6	16.5	19.0	19.9	20.4	23.1	25.8	26.6	27.5	27.1	25.9	24.2	21.8	18.9	16.4	14.0	9.6	8.5
7	7.7	7.5	7.6	9.4	10.5	12.8	15.5	16.6	19.0	20.0	21.5	23.3	26.0	26.7	27.9	27.0	25.9	24.1	21.5	18.7	16.8	13.8	10.2	8.4
8	7.7	7.5	7.7	9.6	11.2	13.0	14.8	16.7	18.2	20.0	21.9	23.4	26.1	26.7	28.0	26.9	25.2	24.0	21.4	18.5	17.0	13.5	8.9	8.3
9	6.9	7.5	6.8	9.7	10.5	13.2	14.8	16.9	17.7	20.1	22.2	23.6	26.3	26.8	27.7	26.8	24.8	23.9	21.0	18.3	16.4	13.3	9.1	8.3
10	6.9	7.5	7.7	9.8	10.7	13.3	14.8	17.0	18.4	20.2	22.0	23.7	26.1	26.8	27.7	26.8	25.2	23.8	21.3	18.1	15.0	13.0	10.8	8.2
11	7.0	7.6	7.4	9.9	10.8	13.5	15.7	17.2	19.2	20.3	21.8	23.9	26.8	26.9	27.3	26.7	25.3	23.6	20.8	18.0	15.3	12.8	11.6	8.1
12	6.8	7.6	9.0	10.0	11.5	13.7	16.1	17.2	19.0	20.4	22.6	24.0	26.4	26.9	27.6	26.6	25.3	23.5	20.3	17.8	14.8	12.6	10.9	8.0
13	7.1	7.6	10.5	10.1	11.6	13.8	15.7	17.3	19.6	20.5	22.0	24.2	25.7	27.0	27.8	26.5	25.0	23.3	19.7	17.7	15.5	12.5	9.6	7.8
14	7.4	7.6	10.2	10.1	11.5	13.9	16.2	17.4	19.4	20.6	22.2	24.3	26.2	27.0	27.6	26.4	24.8	23.2	19.5	17.5	15.6	12.3	9.5	7.7
15	8.6	7.6	9.7	10.2	11.6	14.0	16.5	17.5	19.6	20.7	22.3	24.5	25.4	27.1	27.4	26.4	25.2	23.0	19.8	17.4	15.0	12.1	9.0	7.7
16	8.4	7.6	8.9	10.3	12.5	14.2	16.4	17.7	20.1	20.8	22.4	24.6	25.6	27.1	27.3	26.3	24.9	22.8	20.1	17.2	14.4	12.0	8.9	7.6
17	8.1	7.7	8.3	10.4	13.1	14.3	16.2	17.8	20.4	20.9	21.9	24.7	25.9	27.2	27.0	26.2	25.5	22.7	19.4	17.0	15.0	11.8	7.2	7.5
18	7.7	7.8	8.2	10.5	13.9	14.4	16.2	17.9	20.0	20.9	22.2	24.9	26.0	27.3	26.4	26.1	25.7	22.4	19.4	16.9	15.4	11.6	5.9	7.5
19	7.8	7.8	9.9	10.7	14.1	14.5	16.5	18.0	20.0	21.0	22.8	25.0	26.9	27.3	26.5	26.1	24.4	22.2	19.2	16.7	14.3	11.3	7.2	7.6
20	7.8	7.9	10.8	10.8	12.5	14.6	16.9	18.2	20.1	21.1	22.5	25.1	26.8	27.4	27.0	26.0	23.7	22.0	18.1	16.6	13.4	11.1	8.2	7.7
21	7.3	7.9	9.9	10.9	13.4	14.7	17.4	18.3	19.3	21.2	23.2	25.2	26.9	27.4	27.6	26.0	23.6	21.9	18.1	16.5	13.6	10.8	9.5	7.7
22	8.4	7.9	10.7	11.0	12.4	14.8	16.9	18.4	19.2	21.3	23.5	25.3	26.7	27.3	27.7	25.9	24.2	21.8	18.9	16.4	14.9	10.6	8.9	7.6
23	8.7	8.0	10.0	11.1	12.4	15.0	16.2	18.5	20.1	21.4	23.8	25.5	26.7	27.3	27.4	25.8	23.6	21.5	18.8	16.2	14.0	10.3	8.2	7.6
24	6.4	8.0	8.3	11.2	12.0	15.1	16.9	18.6	20.3	21.5	24.2	25.6	26.6	27.3	27.2	25.6	22.8	21.3	17.3	16.0	12.4	10.2	8.7	7.5
25	5.4	8.2	9.2	11.4	12.2	15.3	17.2	18.7	21.2	21.6	23.8	25.7	26.9	27.4	27.2	25.5	23.2	21.2	16.9	15.9	12.1	10.1	8.6	7.5
26	7.1	8.4	9.6	11.5	13.4	15.5	17.4	18.8	20.6	21.7	24.4	25.8	26.9	27.4	26.6	25.4	23.6	21.0	17.6	15.8	13.2	9.9	8.1	7.5
27	7.8	8.5	9.2	11.6	13.5	15.6	16.9	18.9	21.3	21.8	24.0	25.8	27.1	27.4	26.4	25.3	23.5	20.8	18.5	15.7	13.0	9.8	8.0	7.5
28	8.0	8.5	10.0	11.7	13.6	15.7	17.3	19.0	21.0	21.9	24.5	25.9	27.6	27.4	26.5	25.2	23.3	20.6	18.0	15.4	12.2	9.6	6.7	7.4
29	7.5	8.5	11.3	11.8	14.2	15.8	17.6	19.2	21.1	22.0	24.8	26.0	27.4	27.4	26.4	25.1	23.2	20.4	17.3	15.2	11.6	9.5	7.2	7.4
30	7.9	8.6			15.1	16.0	18.0	19.3	21.1	22.1	25.0	26.1	27.4	27.4	26.4	25.0	23.3	20.2	16.3	15.1	12.0	9.3	7.5	7.4
31	7.2	8.6			14.9	16.0			20.6	22.2			27.4	27.4	26.4	24.9			15.9	15.0			7.3	7.4

構造体強度補正值28Sの標準値（セメントの種類:普通ポルトランドセメント）				暑 中コンクリート（修 正 標 準 配 合）適 用 期 間	
構造体強度補正值	コンクリートの打込みから材齢28日までの期間の 予想平均気温θの範囲（℃）		コンクリートの打込み期間	構造体強度補正值	日平均気温の平年値が25℃を超える期間
3.0 N/mm ²	8 ≤ θ		1月23日 ～ 12月12日	6.0 N/mm ²	6月30日 ～ 9月18日 （6月下旬 ～ 9月中旬）
6.0 N/mm ²	0 ≤ θ < 8		12月13日 ～ 1月22日		