

気 温 表 (宮崎地方气象台、村所測候所)

「日平均気温・打設後28日間の平均気温」2024年度版

(2014年～2023年)

過去10年

月 日	1月		2月		3月		4月		5月		6月		7月		8月		9月		10月		11月		12月	
	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後
1	3.4	5.0	5.5	6.4	9.0	10.3	13.6	14.6	16.9	18.3	20.6	21.9	23.5	24.9	26.1	25.9	24.3	23.1	21.2	18.1	14.0	12.5	8.8	6.6
2	4.5	5.1	5.8	6.5	8.4	10.4	13.1	14.7	16.4	18.5	20.4	22.0	23.4	25.0	25.9	25.8	24.1	23.0	20.9	18.3	14.3	12.3	7.5	6.4
3	4.5	5.2	5.5	6.6	7.1	10.6	13.4	14.8	16.2	18.7	20.0	22.1	22.9	25.1	25.9	25.8	24.0	22.9	21.0	18.0	13.4	12.1	8.1	6.4
4	5.3	5.2	5.3	6.7	9.0	10.8	14.1	14.9	17.0	18.8	38.5	22.2	23.8	25.2	26.2	25.7	24.1	22.8	21.3	17.7	12.5	12.0	8.9	6.2
5	5.8	5.2	5.0	6.8	10.2	11.0	14.1	15.0	17.6	18.9	19.4	21.7	24.2	25.3	26.1	25.7	24.2	22.7	21.3	17.5	12.7	11.8	7.7	6.0
6	5.9	5.2	4.7	6.9	9.3	11.1	14.1	15.1	17.0	19.0	19.7	21.8	24.0	25.4	25.8	25.6	24.6	22.6	20.2	17.2	13.8	11.6	7.3	5.9
7	5.5	5.2	5.1	7.1	8.7	11.2	13.7	15.2	17.7	19.2	21.2	22.0	24.4	25.4	26.2	25.5	24.6	22.5	19.4	17.0	14.5	11.5	7.1	5.8
8	6.1	5.2	5.4	7.3	9.6	11.4	13.5	15.3	17.5	19.9	21.3	22.1	24.5	25.5	26.5	25.4	24.0	22.3	19.6	16.7	14.7	11.2	5.9	5.7
9	5.1	5.2	4.8	7.4	8.9	11.6	13.6	15.4	17.0	20.0	21.6	22.2	24.6	25.5	26.0	25.4	23.6	22.2	19.7	16.5	13.9	10.9	6.2	5.7
10	4.3	5.2	5.1	7.6	9.2	11.7	13.9	15.6	17.8	20.1	21.4	22.3	24.3	25.6	26.3	25.3	23.8	22.1	20.0	16.3	12.9	10.7	7.7	5.7
11	4.7	5.2	5.1	7.7	9.2	11.9	14.1	15.7	18.5	20.2	20.7	22.4	24.9	25.7	25.9	25.3	23.5	21.9	19.6	16.1	13.0	10.5	9.3	5.7
12	4.6	5.2	6.3	7.9	9.9	12.1	14.4	15.8	17.6	20.3	21.8	22.5	24.9	25.7	25.6	25.2	23.1	21.8	18.9	15.9	12.3	10.2	8.6	5.5
13	4.6	5.2	7.7	8.0	9.8	12.2	13.7	15.9	18.7	20.4	20.9	22.6	24.7	25.8	26.2	25.1	23.1	21.7	18.5	15.7	12.7	10.0	7.3	5.4
14	4.8	5.2	7.7	8.0	10.1	12.3	14.3	16.1	18.6	20.5	20.9	22.8	25.0	25.8	26.1	25.0	23.0	21.5	18.0	15.5	12.5	9.9	7.1	5.3
15	5.2	5.2	7.0	8.1	9.7	12.5	14.6	16.2	18.4	20.6	21.1	22.9	24.9	25.8	25.8	24.9	23.5	21.4	17.4	15.4	11.5	9.8	6.6	5.2
16	5.1	5.3	6.3	8.2	10.8	12.7	14.6	16.4	19.1	20.7	21.1	23.0	24.8	25.9	26.1	24.8	23.4	21.2	18.1	15.2	11.1	9.6	6.3	5.2
17	4.8	5.4	5.9	8.3	11.9	12.8	14.9	16.5	19.5	20.8	20.7	23.2	24.9	25.9	26.0	24.7	23.8	21.0	17.6	15.0	11.6	9.5	5.2	5.1
18	4.7	5.5	5.7	8.5	12.4	12.8	14.9	16.6	18.3	20.8	20.8	23.3	25.3	26.0	25.1	24.6	23.6	20.8	17.0	14.8	12.4	9.3	3.9	5.1
19	4.5	5.6	6.5	8.7	13.2	12.9	15.5	16.8	19.8	20.9	21.5	23.5	25.0	26.0	25.6	24.6	21.9	20.6	16.8	14.6	12.0	9.1	4.9	5.2
20	5.3	5.6	8.0	8.9	12.0	13.0	15.7	16.9	19.5	21.0	21.7	23.6	25.3	26.0	26.1	24.5	21.2	20.4	16.1	14.4	11.6	8.8	4.9	5.2
21	4.1	5.6	7.1	9.1	11.7	13.1	16.4	17.0	18.4	21.0	21.4	23.7	25.2	26.0	26.1	24.4	21.3	20.3	15.7	14.2	11.4	8.6	6.1	5.2
22	5.2	5.7	7.6	9.3	10.6	13.2	16.3	17.2	18.5	21.1	21.7	23.8	25.7	26.0	26.3	24.3	22.1	20.1	16.8	14.1	12.7	8.3	6.8	5.2
23	6.4	5.7	8.1	9.5	10.5	13.4	14.4	17.3	19.0	21.2	22.1	24.0	25.7	26.0	25.9	24.2	22.1	19.9	16.2	14.0	12.3	8.1	5.7	5.1
24	4.7	5.8	6.4	9.5	10.2	13.6	14.9	17.4	19.1	21.3	22.8	24.1	26.0	26.0	25.5	24.0	21.4	19.7	15.1	13.8	11.4	7.8	6.2	5.2
25	5.0	5.9	6.9	9.7	10.7	13.8	15.9	17.5	20.4	21.4	22.3	24.2	26.1	26.0	25.3	23.9	22.3	19.5	14.7	13.7	11.0	7.7	6.2	5.1
26	5.8	6.0	8.1	9.8	11.7	14.0	16.2	17.7	19.7	21.4	22.2	24.3	26.0	26.1	25.2	23.7	21.9	19.3	15.1	13.6	11.0	7.5	5.2	5.1
27	5.7	6.1	8.4	9.9	12.2	14.1	15.9	17.8	19.9	21.5	22.3	24.4	26.1	26.0	25.2	23.6	22.1	19.1	15.4	13.5	11.2	7.3	4.9	5.1
28	5.7	6.1	8.5	10.0	12.4	14.2	15.6	17.9	19.6	21.6	23.5	24.6	26.6	26.0	25.1	23.5	22.0	18.8	15.2	13.4	10.3	7.1	4.5	5.1
29	5.8	6.1	8.4	10.2	12.5	14.3	15.6	18.1	21.2	21.7	23.7	24.7	26.4	26.0	24.8	23.4	21.4	18.5	15.7	13.2	9.8	6.9	4.8	5.1
30	6.5	6.2			13.2	14.4	16.0	18.2	21.2	21.8	23.1	24.7	26.4	25.9	24.9	23.3	21.9	18.3	13.9	12.7	9.7	6.8	5.0	5.1
31	5.2	6.3			12.7	14.5			20.7	21.8			26.3	25.9	24.6	23.2			13.8	12.6			4.5	5.1

構造体強度補正值28Sの標準値 (セメントの種類: 普通ポルトランドセメント)		
温度補正值	打込みから28日までの期間の予想平均気温 θ の範囲 (°C)	コンクリートの打込み期間
3.0 N/mm ²	$8 \leq \theta$	2月14日 ~ 11月22日
6.0 N/mm ²	$0 \leq \theta < 8$	11月23日 ~ 2月15日

暑中コンクリート(修正標準配合)適用期間	
日平均気温が25°Cを超える期間	7月14日 ~ 8月28日
強度補正值: 6.0 N/mm ²	(7月上旬 ~ 8月下旬)