

気 温 表 (宮崎地方気象台、西米良観測所)
過去10年間の西米良地区日平均気温・コンクリート打設翌日から28日間の平均気

作成日:2025年2月
測定期間:2015年～2024年

月	1月		2月		3月		4月		5月		6月		7月		8月		9月		10月		11月		12月		1月
日	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均
1	3.0	5.2	5.6	6.8	8.8	10.3	13.9	14.9	17.0	18.4	20.3	22.0	23.6	25.0	26.4	26.1	24.5	23.3	21.4	18.3	13.9	12.6	8.4	6.7	3.6
2	4.5	5.3	5.5	6.9	7.7	10.4	13.1	14.9	16.4	18.5	20.5	22.1	24.0	25.1	26.5	26.0	24.2	23.2	20.8	18.5	14.6	12.5	8.0	6.5	4.5
3	4.6	5.3	5.2	7.0	6.8	10.6	13.8	15.1	16.2	18.7	20.2	22.2	23.5	25.2	26.3	26.0	24.2	23.2	20.9	18.3	13.9	12.3	8.2	6.4	4.5
4	5.1	5.3	5.8	7.1	9.1	10.8	14.9	15.2	17.1	18.8	38.5	22.3	24.3	25.3	26.7	25.9	24.2	23.1	21.2	18.0	13.2	12.1	8.7	6.3	5.0
5	5.8	5.4	5.7	7.1	10.2	11.0	14.7	15.2	18.0	18.9	19.3	21.8	24.6	25.4	26.6	25.8	24.3	22.9	21.5	17.8	13.1	11.9	7.9	6.1	5.5
6	6.3	5.3	5.3	7.2	10.0	11.1	14.7	15.3	17.4	19.0	19.4	22.0	24.7	25.5	25.9	25.7	24.7	22.8	20.6	17.5	13.5	11.7	7.7	6.0	6.2
7	5.4	5.3	5.4	7.4	9.0	11.3	14.4	15.4	18.0	19.1	20.9	22.2	25.0	25.5	26.5	25.7	24.7	22.7	20.1	17.3	14.4	11.5	7.5	5.9	5.4
8	5.5	5.3	5.3	7.6	9.9	11.5	13.7	15.5	17.4	19.9	21.0	22.3	24.9	25.6	26.6	25.6	24.0	22.6	20.0	17.0	14.7	11.3	6.1	5.8	5.7
9	5.0	5.3	4.8	7.7	8.9	11.6	13.9	15.6	16.6	19.9	21.4	22.4	24.9	25.7	26.2	25.5	23.8	22.5	19.7	16.8	13.9	11.1	6.1	5.8	4.9
10	4.8	5.3	5.4	7.9	9.2	11.8	13.7	15.8	17.5	20.0	21.5	22.5	24.5	25.7	26.6	25.5	24.1	22.3	19.9	16.6	12.9	10.8	7.6	5.8	4.1
11	4.9	5.4	5.4	8.0	9.5	12.0	13.9	15.9	18.5	20.2	20.8	22.7	25.0	25.8	26.2	25.4	23.7	22.2	19.3	16.4	13.4	10.6	8.8	5.7	4.5
12	4.9	5.4	6.5	8.2	9.9	12.2	14.5	16.0	17.6	20.2	21.6	22.8	25.1	25.8	25.9	25.3	23.4	22.0	18.6	16.2	12.2	10.3	8.6	5.6	4.7
13	5.1	5.4	8.1	8.3	9.4	12.3	13.9	16.1	18.8	20.4	21.1	22.9	24.6	25.9	26.3	25.2	23.8	21.9	18.1	16.0	13.3	10.2	7.5	5.4	4.7
14	5.2	5.4	8.2	8.3	10.3	12.5	14.4	16.3	18.9	20.5	21.1	23.1	24.9	25.9	26.3	25.2	23.5	21.8	18.3	15.8	13.4	10.0	7.3	5.3	4.9
15	5.9	5.4	7.9	8.4	10.1	12.6	15.0	16.4	18.4	20.5	21.2	23.2	24.6	26.0	25.9	25.1	24.0	21.6	18.1	15.7	12.6	9.8	6.9	5.2	5.5
16	5.3	5.4	7.0	8.4	10.8	12.8	15.1	16.5	18.8	20.7	21.6	23.3	24.7	26.0	26.3	25.0	23.7	21.4	18.9	15.5	12.0	9.7	6.3	5.1	4.7
17	5.1	5.5	6.3	8.6	11.9	12.9	15.0	16.7	19.5	20.7	21.1	23.4	24.9	26.1	26.0	24.9	23.9	21.2	18.3	15.3	12.6	9.5	5.5	5.1	4.7
18	5.3	5.6	6.3	8.7	12.3	13.0	14.9	16.8	18.4	20.8	21.2	23.6	25.3	26.1	25.2	24.8	24.0	21.0	17.6	15.1	13.1	9.3	4.1	5.1	5.0
19	5.3	5.7	7.5	8.9	12.5	13.1	15.5	16.9	19.7	20.9	21.7	23.7	25.2	26.2	25.5	24.8	22.7	20.8	17.5	14.9	12.5	9.0	5.1	5.1	5.3
20	5.9	5.8	9.2	9.1	11.4	13.1	15.7	17.1	19.8	21.0	21.4	23.8	25.7	26.2	26.2	24.7	22.1	20.6	16.3	14.7	11.9	8.8	4.7	5.1	5.8
21	4.9	5.8	8.1	9.2	11.6	13.3	16.5	17.2	18.5	21.0	21.9	23.9	25.5	26.2	26.3	24.6	21.9	20.5	15.7	14.6	11.6	8.5	6.5	5.1	4.8
22	5.5	5.8	8.8	9.3	10.8	13.4	16.8	17.3	18.4	21.1	21.9	24.1	25.9	26.2	26.5	24.5	22.3	20.3	17.0	14.5	12.3	8.3	6.7	5.0	5.2
23	6.3	5.9	8.5	9.4	10.7	13.6	14.8	17.4	19.0	21.2	22.5	24.2	25.8	26.2	26.1	24.4	22.3	20.1	16.6	14.3	11.9	8.0	5.6	5.0	6.0
24	4.4	6.0	6.5	9.5	10.7	13.7	15.4	17.5	19.2	21.3	23.0	24.3	25.9	26.2	25.8	24.2	21.3	19.9	15.2	14.1	10.7	7.8	5.8	5.0	4.7
25	4.4	6.1	7.1	9.7	11.1	13.9	16.1	17.6	20.6	21.4	22.5	24.4	25.9	26.2	25.5	24.1	22.1	19.7	15.0	14.0	10.2	7.7	5.8	5.0	5.0
26	5.2	6.3	8.0	9.8	11.7	14.1	16.1	17.7	19.8	21.5	22.5	24.5	25.8	26.2	25.2	24.0	22.1	19.5	15.2	13.9	10.8	7.5	5.9	4.9	5.5
27	5.7	6.4	7.8	9.9	11.7	14.3	16.0	17.8	20.2	21.6	22.6	24.7	25.9	26.3	25.1	23.9	22.4	19.3	15.7	13.8	11.1	7.3	5.2	5.0	5.5
28	5.6	6.4	8.0	10.0	12.1	14.4	16.1	18.0	19.6	21.6	23.5	24.8	26.6	26.3	25.1	23.8	22.1	19.0	16.0	13.6	10.0	7.1	4.2	4.9	5.4
29	5.4	6.5	8.8	10.2	12.8	14.5	16.0	18.1	20.8	21.8	23.7	24.9	26.4	26.2	24.9	23.6	21.6	18.8	26.3	13.4	9.1	7.0	4.4	5.0	5.4
30	6.1	6.6			13.1	14.7	16.6	18.3	20.6	21.8	23.5	24.9	26.6	26.2	25.0	23.5	22.1	18.6	14.1	12.9	9.4	6.8	4.9	5.0	6.2
31	5.2	6.7			13.1	14.8			20.3	21.9			26.6	26.1	24.9	23.4			13.7	12.8			4.8	5.0	5.5

構造体強度補正值28Sの標準値 (セメントの種類:普通ポルトランドセメント)			暑 中コンクリート (修 正 標 準 配 合) 適 用 期 間	
構造体 強度補正值	コンクリートの打込みから材齢28日までの 期間の予想平均気温 θ の範囲(℃)	コンクリートの打込み期間	構造体 強度補正值	日平均気温の平年値が 25℃を超える期間
3 N/㎟	$8 \leq \theta$	2月11日 ～ 11月23日	6 N/㎟	7月 7日 ～ 8月30日 (6月下旬 ～ 9月中旬)
6 N/㎟	$0 \leq \theta < 8$	11月24日 ～ 2月10日		