

気 温 表 (宮崎地方気象台、西都観測所)

「日平均気温・打設後28日後の平均気温」

(2014年～2023年)

月 日	1月		2月		3月		4月		5月		6月		7月		8月		9月		10月		11月		12月	
	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後	日平均	28日後
1	5.3	6.9	7.8	8.2	11.2	12.0	15.2	16.1	18.0	19.6	21.2	22.5	24.8	26.4	28.0	27.6	25.9	24.7	22.9	19.9	16.1	14.5	11.1	8.7
2	6.1	7.0	7.5	8.3	10.3	12.1	14.9	16.2	17.9	19.7	21.2	22.6	24.7	26.5	27.9	27.5	25.8	24.6	22.6	19.6	16.0	14.3	9.8	8.6
3	6.5	7.1	7.3	8.5	8.4	12.3	15.1	16.3	17.6	19.8	20.9	22.8	24.6	26.6	27.8	27.5	25.9	24.5	22.8	19.4	15.4	14.2	10.1	8.5
4	7.1	7.1	7.7	8.6	11.0	12.5	16.0	16.4	18.5	20.0	21.1	22.9	25.5	26.7	28.0	27.4	25.9	24.4	23.1	19.2	14.8	14.0	10.8	8.4
5	7.4	7.1	7.0	8.6	11.7	12.6	15.6	16.5	18.9	20.0	20.5	23.0	25.7	26.8	28.0	27.4	25.7	24.3	23.1	18.9	14.8	13.8	9.6	8.1
6	7.7	7.1	6.5	8.7	10.7	12.7	15.5	16.6	18.6	20.1	20.9	23.2	25.4	26.9	27.7	27.3	26.2	24.2	21.6	18.7	16.1	13.7	9.1	8.0
7	7.4	7.1	7.1	8.9	10.3	12.9	15.4	16.7	18.9	20.2	21.9	23.3	25.9	27.0	28.1	27.2	26.3	24.0	21.2	18.4	16.5	13.5	9.2	7.9
8	8.1	7.1	7.4	9.1	10.8	13.1	14.9	16.8	18.5	20.3	22.3	23.5	26.1	27.0	28.1	27.1	25.4	23.9	21.3	18.2	16.9	13.2	8.5	7.8
9	6.8	7.1	6.6	9.2	10.6	13.3	14.7	16.9	18.4	20.4	22.6	23.6	26.3	27.1	27.9	27.1	24.9	23.8	21.1	18.0	16.1	13.0	8.7	7.8
10	6.2	7.1	7.1	9.3	10.9	13.5	15.4	17.1	18.9	20.5	22.3	23.7	26.2	27.2	28.2	27.0	25.2	23.7	21.7	17.8	14.8	12.7	10.3	7.8
11	6.4	7.1	7.0	9.4	10.7	13.6	15.8	17.2	19.4	20.6	22.1	23.9	26.9	27.2	27.5	26.9	25.3	23.5	21.2	17.6	14.9	12.5	11.5	7.7
12	6.5	7.1	8.5	9.6	11.5	13.8	16.2	17.3	19.1	20.7	23.0	24.0	26.7	27.3	27.6	26.8	25.1	23.4	20.8	17.5	14.2	12.3	10.6	7.5
13	6.4	7.1	9.9	9.7	12.3	13.9	15.7	17.4	19.5	20.8	22.2	24.1	26.3	27.3	28.0	26.7	24.5	23.3	20.0	17.3	15.0	12.1	9.0	7.4
14	6.6	7.2	9.3	9.7	11.6	14.0	16.0	17.5	19.7	20.9	22.3	24.3	26.8	27.4	27.9	26.6	24.6	23.1	19.4	17.1	14.5	12.0	8.9	7.3
15	7.5	7.2	8.4	9.8	11.5	14.1	16.2	17.6	19.9	21.0	22.6	24.4	26.2	27.4	27.7	26.6	24.8	23.0	19.0	17.0	13.7	11.9	8.6	7.2
16	7.4	7.2	8.3	9.9	12.4	14.3	16.5	17.7	20.6	21.1	22.4	24.6	26.2	27.5	27.7	26.5	24.8	22.8	19.6	16.8	13.2	11.7	8.8	7.2
17	7.2	7.3	8.0	10.1	13.3	14.4	16.4	17.9	20.9	21.1	21.9	24.7	26.2	27.5	27.5	26.3	25.4	22.6	18.8	16.6	13.9	11.5	7.1	7.1
18	6.6	7.4	7.5	10.2	14.6	14.5	16.6	18.0	20.2	21.2	22.1	24.9	26.3	27.6	26.6	26.2	25.4	22.4	18.7	16.5	14.7	11.4	5.6	7.1
19	6.7	7.4	8.5	10.4	15.0	14.6	16.6	18.1	20.5	21.3	22.7	25.0	26.7	27.6	27.1	26.2	23.7	22.2	18.6	16.3	13.9	11.1	6.8	7.2
20	6.9	7.5	9.4	10.6	13.4	14.6	17.1	18.3	20.5	21.3	23.0	25.2	26.7	27.7	27.4	26.1	23.0	22.0	18.0	16.1	13.3	10.9	7.9	7.2
21	6.2	7.5	8.2	10.8	13.7	14.7	17.4	18.4	19.4	21.4	23.1	25.3	27.0	27.7	27.9	26.0	23.0	21.9	17.9	15.9	13.4	10.6	8.4	7.2
22	7.3	7.6	9.5	11.0	12.3	14.8	17.2	18.5	19.4	21.5	23.3	25.4	26.9	27.7	27.9	25.9	23.9	21.7	18.8	15.8	14.9	10.4	8.6	7.2
23	8.3	7.6	9.8	11.2	12.1	15.0	16.4	18.6	20.2	21.6	23.5	25.5	27.1	27.7	27.7	25.8	23.5	21.5	18.1	15.7	14.3	10.1	7.9	7.1
24	6.3	7.6	8.0	11.3	11.9	15.2	16.7	18.7	20.1	21.7	24.3	25.6	27.1	27.7	27.3	25.6	23.1	21.3	17.0	15.5	12.9	9.9	8.2	7.1
25	6.1	7.7	8.9	11.4	12.2	15.4	17.2	18.8	21.3	21.8	23.8	25.7	27.5	27.7	27.3	25.5	23.5	21.1	16.8	15.4	12.7	9.8	8.4	7.1
26	7.4	7.8	9.7	11.5	13.6	15.5	17.7	18.9	20.9	21.9	24.5	25.9	27.6	27.7	26.8	25.3	23.5	20.9	17.1	15.3	13.1	9.6	7.3	7.0
27	7.2	7.9	9.9	11.6	14.0	15.6	17.1	19.0	21.1	22.0	24.0	26.0	27.6	27.7	26.6	25.2	23.4	20.7	17.9	15.2	13.1	9.4	7.3	7.1
28	7.7	8.0	10.4	11.7	13.9	15.7	17.1	19.2	20.9	22.1	24.8	26.1	27.9	27.7	26.7	25.1	23.3	20.5	17.3	15.0	12.3	9.3	6.7	7.0
29	7.7	8.0	10.5	11.9	14.0	15.9	17.4	19.3	21.7	22.2	25.1	26.2	27.8	27.7	26.4	25.0	23.0	20.3	16.7	14.8	11.9	9.1	7.1	7.0
30	8.4	8.1			15.3	16.0	17.6	19.4	21.9	22.3	24.7	26.3	27.8	27.7	26.4	24.9	23.2	20.1	16.0	14.7	11.8	8.9	7.0	7.0
31	6.8	8.1			14.4	16.1			21.1	22.4			27.7	27.6	26.3	24.8			16.0	14.6			6.2	7.0

構造体強度補正值28Sの標準値 (セメントの種類: 普通ポルトランドセメント)		
温度補正值	打込みから28日までの期間の予想平均気温θの範囲(°C)	コンクリートの打込み期間
3.0N/mm ²	8 ≤ θ	1月28日～12月7日
6.0N/mm ²	0 ≤ θ < 8	12月8日～1月27日

暑中コンクリート(修正標準配合)適用期間	
日平均気温が25°Cを超える期間	
強度補正值: 6.0N/mm ²	7月4日～9月18日